

Appl. No. 10/614,373
Amdt. Dated
Reply to Office Action of September 27, 2005

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A magnetic recording medium obtained by coating, on a non-magnetic support, a magnetic coating material having a magnetic powder and binder dispersed in a solvent, wherein said binder contains two kinds of polyurethane resins, one of the polyurethane resins being such as:

an aromatic polyester polyurethane resin obtained by urethanization of an aromatic polyester with an aromatic diisocyanate; and

a polyurethane resin obtained by urethanization of a glycol having a molecular weight of 60 to 250 with an aromatic diisocyanate under a condition ensuring a urethane group concentration of 3.0 mmol/g or above.

said aromatic polyester polyurethane resin has an OH value of 10 to 500 KOH mg/g.

said aromatic polyester polyurethane resin and said polyurethane resin contain any one of metal sulfonate, tertiary amine or quaternary ammonium salt, and said binder contains an aromatic isocyanate hardener.

2-8 Cancelled.